
ARMINANO





Zinc Sulfide Nanoparticles ZSN404

Description:

Zinc sulfide is an inorganic compound with crystal structure of sphalerite and wurtzite. Both sphalerite and wurtzite are intrinsic, wide-band gap semiconductors. Nanostructures of ZnS take a wurtzite phase at lower and higher temperatures. ZnS has a band gap of 3.66 eV at 300 K, negative conductivity and a small exciton Bohr radius of about 2.5 nm. Particle size reduction has a tremendous effect on the properties of ZnS, such as a blueshift in the optical absorption spectrum, increased luminescence, and enhanced oscillator strength, non-linear optical effects, geometrical structure, chemical bonds, ionization potential, mechanical strength, and melting point.

Characterization	
CAS	1314-98-3
Stock No.	ZSN404
Molecular formula	ZnS
Molecular weight (g/mol)	97.46
Form	Powder
Color	White Cream
Morphology	Spherical
Crystal structure	Hexagonal wurtzite
Size range (nm)	5-10
Total impurity (%)	N/A
Density (g/cm3)	4.079
Solubility	Insoluble



Image of zinc sulfide nanopowder (ZSN404)

Note: product specifications are subject to amendment and may change over time.

Applications (but not limited to the following):

In electronic or optoelectronic applications such as in flat-panel displays, white light LEDs, electroluminescent devices, sensors, lasers, infrared windows, ultraviolet (UV) lasers, anti-reflection coating on solar cells, for both in vivo and in vitro imaging applications, As a photocatalyst, for degradation of water pollutants, reduction of toxic heavy metals and water-splitting for H2 evolution

Safety:

Avoid breathing dust.

Always use protective gloves

Always use protective gloves and safety glasses.

Wash with soap and water after exposure.

Refer to MSDS prior to handling this material.




Address: Tehran-Damavand road, Pardis technology park, Danesh 1 street, No. 18.1


Postals Code: 1654120931 Telefax: +98 21 7625 1689




ARMINANO



Zinc Sulfide Nanoparticles ZSN404



TEM images of ZNS404



Storage:

Keep it in cool dry place.

Avoid direct sunlight.

Do not freeze.

To disperse nanoparticles sonication could be used.

Shelf life:

When stored as specified the product is stable for at least 6 months.

www.armina-eng.com Sales@armina-eng.com



Address: Tehran-Damavand road, Pardis technology park, Danesh 1 street, No. 18.1

Postals Code: 1654120931 Telefax: +98 21 7625 1689

